

Tradesmans Choice

MF10

GAP FILLER

Acrylic Filler

Applies PINK dries WHITE
Smart Dry Technology
NEVER MISS A GAP!




**NEW PRODUCT
GUIDE**

MACSIM®

MF10: GAP FILLER

PRODUCT Range

 Pink (wet) White (dry) 53TGFP 310mL


Product Characteristics

Composition Smooth Paste

Typical Properties

pH	8,5-9,5
Specific gravity	1,62±0,03 gr/cm ³ (ASTM D 729)
Tack free time	15-60 min (23°C & 50% R.H) (ASTM C 679)
Curing rate	2mm/ day (23°C & 50% R.H)
Shore A hardness	40-70 Shore A
Volume shrinkage	%32 (ASTM D 412)
Weight loss	%20
Elongation	>%150
Modulus 100% Elongation	≥0,40 Mpa
Max tensile strength	≥0,50 Mpa
Tensile strength	≥0,15Mpa
Temperature resistance	-10°C to +80°C
Application temperature	+5°C to +40°C

APPLICATIONS



Skirting/Architraves



Door frames & Windows

FEATURES & BENEFITS

- Pink turning White on drying
- Very low VOC content
- Waterproof after curing
- Very easy application
- Can be painted
- Can be used on all porous surfaces

SUBSTRATES



Plasterboard



Particle Board



Fibre Cement



Tile



Timber



Plastic



Masonry

Sydney (Head Office)

10 Wonderland Dr
Eastern Creek
NSW 2766
P: (02) 9881 2400
F: (02) 9881 2444

Melbourne

29 Metro Link Cct West
Campbellfield
VIC 3061
P: (03) 9495 7400
F: (03) 9495 7444

Brisbane

36-44 Arshad drive
Berrinba
QLD 4117
P: (07) 3268 5668
F: (07) 3268 6110

Townsville

4/ 13-19 Civil Rd
Garbutt
QLD 4814
P: (07) 4728 2344
F: (07) 4779 4482

Perth

42 Prosperity Ave
Wangara
WA 6065
P: (08) 9308 3800
F: (08) 9308 3880

Adelaide

Unit 4/ 53 Stanbel Rd
Salisbury Plain
SA 5019
P: (08) 8286 0410
F: (08) 8286 0414

Macsim (NZ)

5 Fisher Crescent
Mount Weillington
AUCKLAND 1060
P: (+649) 579 0801
F: (+649) 579 0802